



# FOG COAT

Cal Dorado Fog Coat is a pigmented cement coating designed to achieve color uniformity and help maintain stucco finishes. Cal Dorado Fog Coat is preblended to match each of our colors.

## **SURFACE PREPARATION**

All surfaces must be free of debris, dirt and dust, grease, oils, curing agents, and cleaning solutions. Glossy or painted surfaces must be sanded and cleaned to ensure a proper bond. Repair all pre-existing cracks.

## **MIXING**

1. Combine about 5 qts. (4.73 L) water per each 25 lbs. (11.34 kg) of Cal Dorado Fog Coat and mix with a mechanical mixing device until the mixture is smooth and free of lumps.
2. Let stand for 5 minutes.
3. Add additional water necessary to bring the mixture to a slurry-like consistency.

## **APPLICATION**

Prior to application, test a small area to check color against existing stucco.

**Brush Application:** Using a paint brush, apply Cal Dorado Fog Coat to the target surface, feathering the edges to blend the material with the existing color. Avoid pooling and runs.

**Spray Application:** Using a pressure tank-type sprayer, spray the target surface with light coats of the fog coat. Multiple light coats will produce better results than one heavy coat. Allow approximately 15 minutes drying time between coats. Stir or shake container frequently during application. Avoid pooling and runs.

## **CURING**

Cal Dorado Fog Coat should fully cure in 7 days. Curing time may vary due to ambient temperature or thickness of material.

## **CLEANING**

Clean all tools with water immediately after use.

## **COVERAGE**

Coverage will vary depending on application method. Approximate coverage per 25 lb. (11.34 kg) bag: 1000 – 2000 sq. ft. (92.9 – 185.8 m<sup>2</sup>).

## **PACKAGING**

- Cal Dorado Fog Coat is packaged in 25 lb. (11.34 kg) pails.
- 30 colors to choose from.

## **LIMITATIONS**

Do not apply Cal Dorado stucco when the ambient and surface temperature is below 40°F/4°C. Do not apply to substrates which are frozen or contain frost/ice. Do not apply Cal Dorado stucco in the rain or when rain is expected within 48 hours. In excessively hot or dry conditions, a light spray of clean water is recommended over the stucco finish to prevent cracking. DO not add any other materials to the mixture of Cal Dorado stucco products. Failure to follow these instructions could result in cracking, chipping, discoloration, or peeling. Due to job conditions beyond the control of Western States Wholesale, Inc. we make no warranty as to the acceptance of the final color.

## **SAFETY**

Contains Portland cement. Wear rubber gloves and eye protection. Avoid eye contact or prolonged contact with skin. If eye contact occurs, flush with water for 15 minutes. Consult physician immediately. This product contains free silica. Do not breathe dust; wear NIOSH approved respirator.

**KEEP OUT OF REACH OF CHILDREN.  
DO NOT TAKE INTERNALLY.**